

### PRODUCT DESCRIPTION

Dymonic® 100 is a single-component, medium-modulus, non-sag polyurethane sealant. Dymonic 100 offers a high-performance, high-movement, durable, flexible seal that performs excellently in moving joints and exhibits tenacious adhesion to substrates once fully cured.

### BASIC USES

Typical applications for Dymonic 100 include expansion and control joints, precast concrete panel joints, perimeter caulking (windows, doors, and panels), aluminum, masonry, and vinyl siding. Dymonic 100 is also an excellent choice as a fluid applied flashing material in rough opening perimeters for fenestration/window, door and curtain wall applications. Dymonic 100 is suitable for water immersion applications and will not out gas.

### FEATURES & BENEFITS

Dymonic 100 has been formulated with an innovative polymer technology, similar to TREMproof® 250GC and Vulkem® 45SSL, that allows it to be highly versatile and grants its unique capability to adhere to damp or green concrete without outgassing. The skin time of Dymonic 100 is 2 hours and the tack-free time is 6 to 8 hours. This significantly reduces dirt attraction and improves the overall aesthetic look.

Dymonic 100 has a movement capability of +100/-50% in typical field conditions with excellent performance in moving joints. The formula is low-VOC and UV-stable, meaning Dymonic 100 will not crack, craze, or yellow under extreme UV exposure. Additionally, Dymonic 100 is jet fuel-resistant and compatible with many common construction substrates.

- Compatible with and can be coated over with Tremco's Vulkem Deck Coatings, ExoAir® Air Barrier products and the cold, fluid-applied TREMproof® line of below-grade waterproofing products
- Accepted for use over Nudura Insulated Concrete Forms (ICF)

There are 21 standard color options available for Dymonic 100, with the option of painting over the sealant.

Dymonic 100 meets or exceeds the requirements of the following specifications:

- ASTM C920 Type S, Grade NS, Class 50, Use NT, T, M, A, O, I
- U.S. Federal Specification TT-S-00230C, Class A, Type II
- CAN/CGSB-19,13-M87
- International Code Council (ICC) Section R703.8 Flashing
- AAMA 714-15 Specification for Liquid-Applied Flashing
- NFPA 285 Listed Component

Accepted fire rated systems: FF-D-1186, FW-D-1117, HW-D-1122, WW-D-1200, and BW-S-0006

### AVAILABILITY

Immediately available from your local Tremco Sales Representative, Tremco Distributor, or Tremco Warehouse in 10.1 oz (300 mL) cartridges and 20 oz (600 mL) sausages.

### COLORS

Available in Almond, Aluminum Stone, Anodized Aluminum, Beige, Black, Bronze, Buff, Dark Bronze, Gray, Gray Stone, Hartford Green, Ivory, Light Bronze, Limestone, Natural Clay, Off White, Precast White, Redwood Tan, Sandalwood, Stone, and White.



## LIMITATIONS

Use with adequate ventilation. Always utilize the accompanying SDS for information on Personal Protective Equipment (PPE) and Health Hazards. Not recommended for use in chlorinated, potable, heavy or waste water. Although Dymonic 100 is paintable, this does not imply adhesion to and compatibility with all paints. Consult Tremco Technical Bulletin No. S-09-05 or Tremco Technical Services for more information.

## WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL RESULTS
Rheological Properties	ASTM C639	Non-sag (NS), 0" of sag in channel
Hardness Properties	ASTM C661	40 ± 5
Weight Loss	ASTM C1246	Pass
Skin Time	ASTM C679	2 to 3 hr
Tack Free Time	73.4°F (23°C) 50% RH	6 to 8 hr
Stain and Color Change	ASTM C510	Pass
Adhesion to Concrete	ASTM C794	35 pli
Adhesion to Concrete After Immersion	ASTM C794	30 pli
Adhesion to Green Concrete	ASTM C794	>25 pli
Adhesion to Damp Concrete	ASTM C794	>20 pli
Effects of Accelerated Aging	ASTM C793	Pass
Movement Capability	ASTM C719	± 50%
Movement Capability	ASTM C719 (Modified)	+100/-50%
Tensile Strength	ASTM D412	350 to 450 psi
% Elongation	ASTM D412	800 to 900%
Modulus at 100%	ASTM D412	75 to 85 psi
Tear Strength	ASTM D412	65 to 75 psi
Service Temperature		-40 to 180 °F (-40 to 82 °C)
Application Temperature		40 to 100 °F (4 to 37 °C) *
Smoke Development, Fire Spread	ASTM E84	5, 5
Smoke Development, Fire Spread	CAN S102	10, 10
Fire Resistance of Assembly	NFPA 285	Pass
Crack Bridging	ASTM C1305	Pass
Nail Seal Ability	ASTM D1970 Section 7.9	Pass

\*For temperatures below 40 °F, please refer to the Technical Bulletin, Cold Temperature Sealant Application Recommendations.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

**NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.**

D100-DS/1122



Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



[tremcosealants.com](http://tremcosealants.com) | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122  
800.321.7906 | [tremcocpg.com](http://tremcocpg.com)