

---

### PRODUCT DESCRIPTION

TREMPRO® 830+ is a high performance exterior elastomeric sealant, designed to adhere to a variety of substrates that are commonly found in professional siding and window installations and manufacturing. It demonstrates superior physical properties regarding adhesion, vibration, movement, shear strength and weatherability. It provides a long-lasting elastomeric seal which helps to prevent water and air intrusion. It will not wash out when exposed to rain prior to full cure. Crackproof, waterproof and weatherproof. It is important to note that this sealant is self-tooling, paintable and passes VOC regulations.

---

### BASIC USES

For siding applications, use with sill trim, flashings, fascia, J-trim, F-channel, and crown molding. Also used for sealing the perimeters of wood, PVC, and aluminum residential windows and doors.

Typical substrates include metals, plastic, wood, foam, vinyl, drywall, glass, fiber cement, concrete, mortar, brick, stone, fiberglass, stucco, most common building materials. Manufacturing applications include but are not limited to vehicles, RV's, cargo trailers, semi-trailers, truck bodies, steel tanks, HVAC units, boats, metal buildings, modular construction, cabinets. In glazing applications, TREMPRO® 830+ is used for face bedding, cap beads and sealing miter joints and mulling in window profiles.

---

### FEATURES & BENEFITS

- VOC Compliant
- Self-tooling
- Applies at temperatures as low as 20 °F (-7 °C)
- Extremely flexible – crack proof
- Waterproof & weatherproof
- Paintable after cure
- Excellent UV stability
- For exterior applications
- Wide service range for manufacturing and in-plant construction

---

### PACKAGING

10.1-oz (300-mL) cartridges – clear and translucent

10.1-oz (300-mL) sausages – clear

20.3-oz (600-mL) sausages - clear

---

### AVAILABILITY

Immediately available from your local Tremco Field Representative, Tremco Distributor or Tremco Warehouse.

---

### COLORS

Clear and Translucent

---

### LIMITATIONS

- Application temperature range is between 20 °F (-7 °C) and 120 °F (37.8 °C)
- Not for butt joints less than ¼" wide or joints exceeding ½" wide x ½" deep
- If joint depth exceeds ½", use foam backer rod
- Recommended bead size: 1/4" to 3/8"
- Apply a convex sealant bead to joint ensuring sealant contacts both surfaces
- Avoid gaps in sealant bead, fill joint and avoid tooling
- Natural shrinkage during cure will leave a flat or concave bead
- Not recommended for continuous underwater use, below grade applications, or for surface defects

- Store below 80°F in dry place for optimal shelf life

## SUBSTRATE PREP

Surface must be sound, clean, and dry. Contact surfaces should be free of loose dirt, dust, oils, and any other contaminants. Tremco generally recommends that air temperatures be 40 °F (5 °C) or above before applying any sealant; TREMPRO 830+ can be applied down to 20 °F (-7 °C). If colder weather is imminent, please refer to the Tremco Guide for Cold Weather Applications at [www.tremcosealants.com](http://www.tremcosealants.com).

## APPLICATION

TREMPRO® 830+ is easy to apply with conventional caulking equipment. Avoid gaps in sealant bead, fill joint and avoid tooling. At 75 °F (23.9 °C), 50% RH, a durable skin will form within 10 to 30 min. Please visit [www.tremcosealants.com](http://www.tremcosealants.com) for complete application instructions.

## WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL RESULTS
Rheological Properties	ASTM C639	0 Flow, No deformation <1/8" (<3.0 mm)
Extrusion Rate	ASTM C661	Pass
Hardness Properties	ASTM C661	20 to 30
Weight Loss	ASTM C679	9%
Skin Time	ASTM C679	30 minutes
Tack Free Time	73.4°F (23°C) 50% RH	5 to 10 minutes
Stain and Color Change	ASTM C510	No visible color change, No stain
Adhesion to Aluminum	ASTM C794	11 to 12 pli (2.0 kN/M)
Adhesion to Wood	ASTM C794	15 to 17 pli (3.0 kN/M)
Adhesion to PVC	ASTM C794	15 to 17 pli (3.0 kN/M)
Adhesion to Glass	ASTM C794	15 to 17 pli (3.0 kN/M)
Effects of Accelerated Aging	ASTM C793	Pass

Tremco Commercial Sealants & Waterproofing | [tremcosealants.com](http://tremcosealants.com)

MoYr/DOCCODE

3735 Green Rd  
Beachwood OH 44122  
216.292.5000 / 800.321.7906

1451 Jacobson Ave  
Ashland OH 44805  
419.289.2050 / 800.321.6357

220 Wicksteed Ave  
Toronto ON M4H1G7  
416.421.3300 / 800.363.3213

1350 Gay-Lussac, Unit: 3  
Boucherville QC J4B 7G4  
514.521.9555

